

SCANGRIT

TECHNICAL DATA SHEET

Product: Iron Silicate

Description An inert synthetic mineral blasting abrasive manufactured by granulation in water of the slag arising from unique fumed copper smelting processes. It is essentially an iron silicate with trace metals bound in an amorphous glass in the form of complex silicates and oxides and contains no free silica. The iron is present as iron silicate in amorphous glass (Si(Fe,Al,Ca)O_{2,3}, fayalite Fe₂SiO₄) with accessory magnetite (Fe₃O₄).

Uses As a non-metallic blasting abrasive

Physical Properties:

Specific Gravity (reference water at 20°C)	3.3
Bulk density	1700 kg.m ⁻³
Hardness	7 Mohs
Grain Shape	Angular

Chemical Properties

Typical Chemical Analysis

Silica as	SiO ₂	33-38%	Aluminium as	Al ₂ O ₃	3-7 %
Iron as	FeO	43-55%	Titanium as	TiO ₂	1%
Magnesium as	MgO	1-2%	Calcium as	CaO	1-4%
Zn as	Zn	1-2%	Cu as	Cu	0.5-0.9
Pb as	Pb	0.01-0.2%*	Free silica		<0.5%

*Lead content of Grade 2, 3 and 4 is typically less than 0.04%

Water soluble chloride content - typically <15ppm

Conductivity of aqueous extract - typically < 15 mS/m

Grades

Grade	size range (mm)	Surface profile achieved on mild steel (ISO 8503)
1	0.1 - 0.40	Less than fine
2	0.2 - 0.85	Fine
3	0.2 - 1.70	Medium
4	0.5 - 2.00	Coarse
5	0.2 - 2.5	Coarse
6	0.5 - 2.5	Coarse

Industry Standards

Complies with BS EN 11126 Part 3 - Preparation of Steel Substrates before application of paints and related products – Specifications for non-metallic abrasives Part 3 Copper Slag.

Packing

25 kg bags palletised and shrink-wrapped.

Further Information.

Specific enquiries relating to the application and use of iron silicate may be directed to

Scangrit
Eastfield Road,
Immingham, DN40 3NF
United Kingdom
Tel. 01469 554715 Fax. 01469 571644